



Niax* Urethane Additives Guide

Europe, Middle East, Africa & India

A Leader in Urethane Additives

Momentive Performance Materials Inc. (Momentive) offers one of the most trusted and diverse urethane additive (UA) product lines in the industry, ranging from a broad array of silicone stabilizers to a full portfolio of amine and metal based catalysts to a selection of organic-based property modifiers.

Developed in 1962, Niax* brand additives are essential ingredients in polyurethane formulations used to meet customers' specialized processing and performance needs globally. Niax grades include a comprehensive line of silicones, catalysts and process modifiers for polyurethane foam production. Momentive also offers Geolite* modifiers to help flexible slabstock foam producers broaden their offering of foam grades, as well as Fomrez† organometallic tin catalysts.

Momentive is a pioneer in the polyurethanes market and continues to serve customers with leading innovations, creative solutions and excellent application expertise.



*Niax and Geolite are trademarks of Momentive Performance Materials Inc.

†Fomrez is a trademark of Chemtura Corporation used with permission by Galata Chemicals LLC.

Flexible Slabstock Foam

Niax* Silicones																
	Conventional Foam					Low Emission for general use	High Resilience Foam				Polyester Foam			VE		
	Wide Processing Efficiency	Hydrolytic Stability	CO2 Blown Foam	FR Property			General Purpose	Combustion Modified	High Density	MDI Foam	General Purpose	Low VOC/Low Fogging	FR Property		No added Nonylphenolethoxylate	Cell Structure
Niax Silicones														Product Description, Potential Applications and Typical Benefits		
L-570	H		•													Silicone for low density formulations
L-594Plus	M		•													Medium potency silicone for improved skin
L-580	M	•	•													Silicone for low density formulations
L-590	•	M	•	•												Wide processing latitude for all conventional foams
L-595		M		•												Medium-high efficiency silicone for improved foam yield
L-595LV		M		•												Low viscosity, medium-high efficiency silicone for improved foam yield
L-620	•	H			•											Very high efficiency with wide latitude for conventional and FR
L-620LV	•	H			•											Very high efficiency with wide latitude for conventional and FR, lower viscosity
L-650	•	M		•	•											Silicone for liquid CO2 FR formulations, separate metering
L-618	•	M			•											Wide processing FR silicone with medium efficiency
L-680		M	•		•											FR silicone, can be considered for use in activators
L-670	•	M														Silicone for natural based polyol foams
L-690		H	•		•											FR silicone, can be considered for use in activators
SC-240		M	•	•												Standard silicone for continuous and discontinuous slabstock productions
L-598	•	L	•													Wide processing latitude, moderate efficiency for medium to high density conventional foam
L-818	•	M			•	•										Low emission. Wide processing FR silicone with medium efficiency
L-820	•	H			•	•										Low emission. Wide processing FR silicone with medium efficiency
L-895		H		•		•										Low emission. High efficiency silicone for improved foam yield
L-2112						•	•	•	•	•						Low emission, wide processing medium efficiency Universal HR silicone
L-500						•	•	•	•	•						Low emission cell regulating additive for Viscoelastic MDI foams. Can improve dimensional stability of HR/CMHR foams
L-2100							•	•								General Purpose silicone for HR Foam
L-2171							•	•								HR Silicone for PHD and SAN systems
SE-232										•		•	R			General purpose silicone
L-530										•		•	R			Universal ester silicone
L-539											•	•	F			Textile grades
L-537XF										•	•	•	F			Universal ester silicone with fine cells and open cells
L-626														•		Specialty silicone for visco-elastic foams
L-627														•		Low viscosity specialty silicone for viscoelastic foams

VE = visco-elastic foam, VOC = volatile organic compound, FR = flame retardant, HR = high resilience
M = medium, H = high, L = low, R = regular, C = coarse, F = fine

*Niax is a trademark of Momentive Performance Materials Inc.

Flexible Slabstock Foam

Niax* Catalysts														
	Conventional Foam					Stabilising	High Resilience Foam				Polyester Foam			
	Blow	Balanced	Gel	Low Emissions			Blow	Balanced	Gel	Low Emissions	Blow	Balanced	Gel	Low Emissions
Niax Catalysts													Product Description, Potential Applications and Typical Benefits	
A-1	•						•							High efficiency blowing catalyst
A-133	•						•							Dilution of A-1 for easy metering
B-4		•												Balanced catalyst, optimum for square blocks, Flat top or Maxfoam system
B-18		•						•						Balanced catalyst, with longer cream time for Maxfoam process
A-33			•						•					Gel catalyst
SA-200					•									Stabilising amine for low density foams
EF-600		•	•	•				•	•					Low emission gel catalyst, can reduce foam smell
EF-700	•	•		•			•	•		•				Low emission blow catalyst, can reduce foam smell
EF-867								•		•				Low emission balanced catalyst for automotive applications, can reduce foam smell
C-131NPF										•			•	Blowing catalyst for low fogging polyester foam
KST-100NPF											•		•	Balanced catalyst for low fogging polyester foam
DMP												•	•	Gel co-catalyst for polyester foam
Sn Octoate			•					•						Stannous Octoate
D-50	•			•										Blowing catalyst with low DMF content

*Niax is a trademark of Momentive Performance Materials Inc.

Flexible Slabstock Foam

Geolite* Modifiers	Typical Features
GM-206	Additive for soft foam grades at 90-100 TDI index with safe processing
GM-91	Processing aid additive, can promote the production of quality foam with critical formulations, reduces properties gradients
Niax* Processing Additive	Typical Features
DP-1022	Processing aid additive, can improve mechanical properties in filled foams and high resilience foams
Color Stabilizer CS-15	Antioxidant for low density polyether foam
Color Stabilizer CS-16	Antioxidant for polyether foam with improved UV yellowing properties
Color Stabilizer CS-18	Low emission antioxidant for automotive applications required to meet VDA 278 emission test standards
Color Stabilizer CS-22 LF	Antioxidant improving light stability and enhancing flame lamination properties
Color Stabilizer CS-26LF	High efficiency flame bonding agent with antioxidant properties
Flame Lamination Additive FLE-200LF	Additive for flame-laminable foam with improved bonding properties
Foam Hardener FH-300	Additive to enhance foam hardness - can increase tensile, elongation and tear strength
Foam Hardener FH-400	Additive to enhance foam hardness - Can be blended into polyether polyol
DCF	Additive to improve clickability and foam recovery after compression in polyester foam
SC-200	Additive for polyether sea sponge foam



Molded Foam

Niax* Silicones				
	HR TDI	TDI / MDI	HR MDI	
Niax Silicones	Product Description, Potential Applications and Typical Benefits			
L-3001		•	•	High cell opening silicone
L-3111		•	•	High cell opening silicone
L-3415			•	Low emission silicone with high cell opening
L-3418			•	Low emission silicone with high cell opening and finer cells
L-3002		•	•	Medium cell opening silicone
L-3222		•	•	Medium cell opening silicone
L-3416		•	•	Low emission silicone with medium cell opening
L-3639		•	•	Very low emission, medium potency silicone providing good stabilization along with good foam openness
L-3003		•	•	Stabilizing silicone
L-3417		•	•	Low emission; stabilizing silicone
L-2171 (Y-10366)	•	•	•	High efficiency; balanced silicone
L-3620		•		Low potency, low emission silicone for TDI/MDI technology
L-3630		•		Medium efficiency, low emission silicone for TDI/MDI technology
L-3636	•	•		Very low fogging, medium potency surfactant for TM80 technology
L-3640	•	•		High efficiency, low emission silicone for TDI/MDI technology
L-3170	•			High efficiency balanced silicone
L-3360	•			High efficiency balanced silicone
L-3350	•			High stability silicone
L-3555	•			High stability, low emission silicone
L-3558	•	•		Very low emission, medium - high potency silicone for TDI
L-3151	•	•		High efficiency; balanced silicone an excellent candidate to consider for TDI/MDI blends
L-3167	•	•		Cell regulator; co-silicone surfactant for TDI
L-5309	•			High efficiency balanced silicone
L-3184	•			High efficiency balanced silicone

TDI/MDI = typically 80/20 blend / TDI = toluene diisocyanate / MDI = Methylene diphenyl diisocyanate



*Niax is a trademark of Momentive Performance Materials Inc.

Molded Foam

Niax* Catalysts			
	Blow Amine Catalyst	Balanced Amine Catalyst	Gel Amine Catalyst
Niax Catalysts			Product Description, Potential Applications and Typical Benefits
A-1	•		Standard blow catalyst
A-107	•		Delayed action blow catalyst
A-400	•		Delayed action load building (TDI); cell opening blow catalyst; improved flowability (MDI)
A-440	•		Delayed action load building (TDI); cell opening blow catalyst; improved flowability (MDI)
A-4	•		Catalyst for improved surface cure
C-174	•		HR MDI blow catalyst
B-26	•		HR MDI delayed action blow catalyst
C-225		•	Delayed action catalyst; enhanced curing
A-310		•	Balanced potentially cost-effective catalyst; may enhance skin cure (MDI & MDI/TDI)
A-337			• Surface curing catalyst; low mold temperature (MDI & MDI/TDI)
A-300			• Delayed action load building; cell opening gel catalyst (low corrosion)
A-33			• Key gel catalyst
Low Emission Catalyst			Product Description, Potential Applications and Typical Benefits
EF-600		•	• Balanced catalyst; predominantly gel
EF-602		•	• Balanced delayed catalyst; predominantly gel
EF-680		•	• Balanced delayed catalyst; predominantly gel can deliver improved end curing
EF-700	•	•	Balanced catalyst; predominantly blow
EF-705	•	•	Balanced cell opening delayed catalyst; predominantly blow
EF-708	•	•	Balanced catalyst; predominantly blow

HR = High resilience

Rigid Foams

Niax* Silicones								
	Fine Cells	Pentane solubility in Polyols	Blowing agents emulsification	Cell Stabilization	Foam Flow / Density Distribution	FR Properties (DIN 4102)	Void Reduction	
Niax Silicone	Product Description, Potential Applications and Typical Benefits							
L-6895	••••	••••	••	•••	••••	••	••••	High polyol/blowing agent compatibility and low lambda combined with excellent flow and reduced voids formation, also in fast reactive systems, for refrigerators, water heaters and all discontinuous applications
L-6891	••••	•••	••	••••	•••	••	••••	High polyol/pentane solubility - very low lambda value foam and voids reduction, for discontinuous applications especially refrigerators
L-6887	••••	••••	••	••••	•••	••	•••	Best polyol/pentane solubility - can provide very fine cells for discontinuous applications especially refrigerators
L-6884	••••	•••	••	••••	•••	••	•••	Can improve polyol/pentane or HFC's compatibility - can provide very fine cells and good flow, for refrigerators and all discontinuous applications
L-6866	••••	••	••	••••	•••	••	••••	For pentane blown refrigerators and dis-continuous panels to reduce surface voids formation, while still delivering excellent lambda value
L-6988	••••	••	•••	••••	•••	••	•••	Very fine cells with pentane and HFO/HC, increase froth shear stability thus reducing voids formation, good storage stability in acidic condition
L-6900	••••	••	••••	••••	••••	••	•••	Strong emulsifier, fine cells with all blowing agents - continuous and discontinuous applications
SR-321	••	••••	••	••••	•••	•••	•	For HCFC but also HFC's and pentane co-blown with water, good flow and dimensional stability
L-6620	••••	••	•••	••	•••	••	•••	Combination of strong nucleation and emulsification, can resolve compatibility problems and reduce defects due to irregular mixing. Suitable also as co-silicone to improve nucleation.
L-6630	••	•	••	••	••••	••	•••	Reduce foam voids formation in continuous and discontinuous application - effect increase with higher usage level
L-6633	•••	•••	•••	•••	•••	••	•••	Can reduce voids formation and excellent polyol compatibility efficiency can increase with usage level
L-6635	••	•	•	••	•••	••	••••	Premium grade silicone to reduce foam voids and achieve excellent surface quality in metal faced panels PUR and PIR
L-6638	••	••	••	••	•••	••	••••	High performance voids reduction silicone for steel faced sandwich panels with improved polyol compatibility
L-6642	•••	••	••	••	••••	••	•••	Balanced stabilizer with good voids control and flow for both continuous and discontinuous process , suitable for all blowing agents included formic acid and HFOs
L-6643	•••	•••	••	••	••••	••	••••	Combination of voids reduction, high flow and extended shelf life in presence of acids. For all blowing agents including formic acid & HFO's but also pentane and for a variety of applications, continuous, discontinuous and wood-imitation
L-6100	••	••	••	•••	•••	••••	••	Can produce foams with good dimensional stability and improved fire properties, good liquid flow and leveling

HFC = Hydro Fluoro Carbon, **HCFC** = Hydro Chloro Fluoro Carbon, **HFO** = Hydrofluoro Olefin, **PIR** = Polyisocyanurate, **PUR** = Polyurethane,
Features: Strong = ••••, Moderate = •

*Niax is a trademark of Momentive Performance Materials Inc.

Rigid Foams

Niax* Silicones								
	Fine Cells	Pentane solubility in Polyols	Blowing agents emulsification	Cell Stabilization	Foam Flow / Density Distribution	FR Properties (DIN 4102)	Void Reduction	
Niax Silicone	Product Description, Potential Applications and Typical Benefits							
L-6265	••	•••	•••	•••	••	••••	••	Improves dimensional stability and FR for spray and panels application with various water/co-blown technologies
L-5111	••••	•	•••	•	•••	••	••	For boardstock fine cells with pentane blowing agents - for PIR/PUR boardstock lamination
L-5112	••••	••	••••	••	•••	••	•••	For boardstock, improves mixing quality and emulsification of pentane up to high usage level. Improves foam quality and reduces laydown defects
L-5162	••••	••	•••	•••	•••	••	•••	For boardstock, strong nucleation and emulsification power, for n- and iso-pentane and less compatible raw materials
L-5158N	•••	•	•••	••	••••	••	••••	For PIR boardstock, better processing on high speed lines. Better edge stability, reduced surface defects, reduce emulsion viscosity, increase liquid flow
L-5466	••••	••	•••	•••	•••	••	••••	For boardstock, strong nucleation and stabilization can reduce surface voids when using gas-tight facings, help compatibility with APP's
L-5345	••	••	••••	•	•••	••	••	1K/OCF foam, good emulsification also for structural foam, blocks and phenolic foams
L-5348	••	•	•••	••	•••	•	••	1K/OCF foam, also manufactured without HFC, high froth volume, good compatibilization, excellent storage stability
L-5350	•••	•	••••	•	••	••	••	1K/OCF foams. Multipurpose stabilizer mainly for straw foam applications
L-5351	•••	•	••••	•	•••	••	••	1K/OCF foam - can improve foaming at low temperature and is manufactured without HFC
L-5360	•••	•	••••	•	••	••	•••	1K/OCF foams. High yield in gun foams allowing high propellant levels to be used
L-5362	•••	•	••••	•	••	••	•••	1K/OCF foams. High yield for gun foam applications – High dimensional stability over wide temperature range
L-6164	••		••		••	•••		Cell-opener, cell-regulator - very efficient cell opener, OCF/1K and 2K systems
L-6186	••		••	•	••	•••		Open cells rigid foam - also efficient in overpacked conditions and high index - polyether and polyester based, density range 15-200 g/l
L-6188								
L-6190	•••	•	•••	••	••	•	••	Packaging foam & low density spray open cells - good balance froth stabilization and cell opening

1K/OCF = 1 Component foam, **HFC** = Hydro Fluoro Carbon, **PIR** = Polyisocyanurate, **PUR** = Polyurethane, **APP** = Aromatic Polyester Polyols,
Features: Strong = ••••, Moderate = •



Rigid Foams

Niax* Catalysts and Special Additives									
	PUR discontinuous	PIR discontinuous panels	PUR continuous lamination and block	PIR continuous lamination and block	PUR / PIR discontinuous block	Spray	Water blown PUR and PIR foam	Packaging, open cells foam	
Niax Catalysts									
Product Description, Potential Applications and Typical Benefits									
A-1	•	•	•	•	•	•	•	•	Very effective blowing catalyst, promote selectively water-NCO reactions, can improve foam flow and rate of expansion
C-5	•		•	•		•			General purpose blowing catalyst
C-8	•	•	•		•	•	•	•	General purpose PUR catalyst
PM-40			•	•	•				Blowing catalyst based on A-1, moderate odor and viscosity and may be used with direct metering
BDMA	•	•	•		•	•	•	•	Dimethylbenzylamine, weak gel catalyst, can reduce surface friability and can improve foam adhesion in particular with mainly water-blown foams
DMEA	•		•		•	•			Moderate odour, typically cost-effective, reactive catalyst
DMEE	•	•					•	•	Moderate odour, typically cost-effective, reactive catalyst, more blowing efficiency compared to DMEA
DMDEE	•	•			•	•		•	Moderate activity blow catalyst, excellent storage stability also in isocyanate and prepolymers, 1K/OCF foams
PM20 plus			•	•			•	•	Blow-gel catalyst for direct in line metering in the continuous lamination of PUR or for PIR in combination with a potassium catalyst
C-27	•	•	•	•			•	•	Low odor catalyst offering improved shelf life for water co-blown systems
C-31	•	•	•	•			•		Delayed action catalyst for PIR and PUR, improve green strength and surface curing, reduce post expansion in thick panels
C-41	•	•	•	•			•		Strong gel catalyst promoting both PUR and PIR reaction, promote fast crosslinking, can reduce demould time and improve foam adhesion
A-107	•				•		•		Acid blocked delayed action blow catalyst
C-520			•	•					Blowing catalyst formulated for safer handling, it enables an easier balancing of the full catalysts package in PIR continuous production
C-10			•	•	•	•	•	•	Reactive amine catalyst, ideal for spray and open-cell applications. Blowing catalyst giving a smooth reaction profile, good candidate also in flexible moulded foams
C-15	•	•	•	•	•	•	•	•	Reactive amine catalyst, ideal for spray and open-cell applications. Balanced blow-urethane catalyst, good candidate also in flexible foams where it improves skin cure
PO-10			•	•	•				Low viscosity potassium octoate to facilitate in-line metering in continuous lines. Provides crosslinking and cure, maintaining a smooth rise profile and an improved liquid flow.
Potassium Octoate LV			•	•	•				15% K containing PIR catalyst for direct metering (2500 cPs), also good as general purpose curing catalyst in PUR
Potassium Octoate	•		•	•	•				15% K containing PIR catalyst, also good as general purpose curing catalyst in PUR
K-ZERO 3000	•	•	•	•	•	•	•		Potassium Octoate formulated for safer handling, 15% Potassium, 3000 cPs viscosity, PIR catalyst
Potassium Acetate	•		•	•	•	•			15% K containing PIR catalyst
MC-710/MC-810						•		•	Bismuth based catalysts, exhibiting strong gel catalytic activity.
Niax Special Additives									
Product Description, Potential Applications and Typical Benefits									
RA-1		•	•				•		Can speed up foam hardening and adhesion without influencing gel time, in particular for PIR foam made with aromatic polyester polyols
AP-01	•	•	•	•			•		Adhesion promoter additives, reduce surface friability in high water and/or high index formulations

NCO = Isocyanate, **PU** = Polyurethane, **1K/OCF** = 1 Component foam, **HFC** = Hydro Fluoro Carbon, **PIR** = Polyisocyanurate, **PUR** = Polyurethane, **APP** = Aromatic Polyester Polyols

*Niax is a trademark of Momentive Performance Materials Inc.

Specialty Applications

Niax* Silicone and Modifiers							
	Microcellular (Polyether)	Microcellular (Polyester)	SRIM/Composite	Integral Skin Foam	PU Leather/Coatings	Mechanical Froth	
Product Description, Potential Applications and Typical Benefits							
L-1500	•	•		•			Standard surfactant for microcellular systems
L-1501		•		•			Wide-processing latitude with excellent open cell for low-medium density systems
L-1507	•	•					For low-density polyester or polyether-based microcellular systems with excellent emulsification
L-1541		•	•				For high-density polyester-based microcellular systems with thick skin and SRIM applications
L-6913	•		•	•			General purpose surfactant for polyether shoe sole and rigid foam systems, low freezing point
L-5302	•		•	•			Medium stabilizing surfactant developed for integral skin and high-density polyether-based microcellular systems
L-1111						•	Promotes adhesion between organic and inorganic in water, solvent based PU coat and acrylic coating application, Epoxy functional group
L-1128						•	Low surface tension silicone for Dry process PU Leather Coating, stable in pH 4-10, provides excellent wetting, leveling and dispersion
L-1131						•	Cell stabilizer for wet process PU leather, provides good deposition, increases thickness, speeds up DMF and water exchange
L-1151						•	Industry standard, provides uniform medium cell structure in wet process PU leather
L-1160						•	Linear reactive silicone, enhance anti-sticking property, good solubility in PU system. Improves leveling in coating application
L-1169						•	Linear reactive silicone, enhance anti-sticking property, good leveling, and silky hand feeling
L-5614						•	Industry-standard surfactant for the mechanically frothed foam process
L-5617						•	Zero VOC surfactant analog of L-5614 used in the mechanically frothed foam processes
L-5639						•	A low VOC mechanical froth surfactant, non-hydrolysable, provides high closed cell content while reducing both froth density and shear induced cell collapse

Specialties Applications Catalysts												
	Microcellular/Shoe Sole	SRIM/Composite	Elastomers	Spray Elastomer	Integral Skin Foam	PU Leather/Coatings		Urea Selectivity	Urethane Selectivity	4=better		
Product Description, Potential Applications and Typical Benefits									Pot Life	Curing Speed	Hydrolysis Stability	
A-100	•	•	•	•	•	•	TEDA Crystals		•	1	4	4
A-400	•	•			•		Delayed-action, blowing-selective catalyst for open-mold pouring applications	•		2	3	4
A-440	•	•			•		Delayed-action, blowing-selective amine catalyst developed for microcellular foams	•		2	2	4
A-533	•	•	•	•	•	•	Industry-standard TEDA catalyst in (mono)ethylene glycol		•	1	4	4
A-525	•	•	•	•	•	•	Industry-standard TEDA catalyst in BDO		•	1	4	4
A-534	•	•	•	•	•		Delayed action, improve flow, demold and mechanical properties		•	3	2	4
A-535		•	•			•	Delayed-action gel catalyst for microcellular/SRIM/PUL applications		•	3	3	4
A-537	•	•	•		•		Delayed-action TEDA-based catalyst for open-mold pouring applications		•	3	2	4
A-575	•	•	•		•		DBU based Temperature-activated, delayed-action, powerful, gelling-selective catalyst		•	3	2	4
A-577		•	•		•		Delayed-action, powerful, gelling-selective catalyst		•	3	2	4
MC-710	•	•		•	•	•	Tin free metal based catalysts, strong gelling, can replace DBTDL		•	1	4	2
LC-5635		•				•	Heat activated catalyst Sn/Hg/Ni free.		•	4	1	2
LC-5636		•	•			•	Heat activated catalyst Sn/Hg/Ni free. Lower activation temperature compared to LC-5635		•	3	2	2

Customer Service Centers

Email

commercial.services@momentive.com

Telephone

Americas

+1 800 295 2392

+1 614 986 2495

Europe, Middle East, Africa and India

00800 4321 1000

+40 212 534754

Asia Pacific

China

800 820 0202

Japan

+81 276 20 6182

All Other Countries

+60 3 9206 1543

To find a specific language, visit the Contact Us page at Momentive.com. You may select a country to view additional languages and the corresponding telephone numbers.

For email inquiries, we will make every attempt to respond in the incoming written language. If that is not possible, we will respond in English.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Niax, Geolite, Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.



260 Hudson River Road
Waterford, NY 12188 USA
momentive.com