

SAG™ 770 Antifoam

Description

SAG 770 antifoam rapidly controls aqueous foams and continues to inhibit foams in protein and starch solutions. This product combines the efficient durability of traditional silicone antifoams with the quick knockdown of organic defoamers.

Key Features and Typical Benefits

- Increased production throughput in food processing applications
- Rapid knockdown of existing foam
- Long-term foam inhibition in protein and starch solutions
- Superior dispersibility in the foaming media
- Excellent aqueous dispersibility
- Halal Certified ⁽¹⁾

(1) This product is produced under the supervision of the Islamic Food and Nutrition Council of America (IFANCA). This product is in compliance with the halal requirements under Islamic laws.

Typical Physical Properties

| | |
|----------------------------------------|-----------------|
| Appearance | White |
| Form | Pourable liquid |
| Specific Gravity at 25/25°C | 1.0 |
| Viscosity at 25°C (after stirring), cP | 1000-2000 |
| pH | 5 |
| Suitable Diluent | Water |
| Shelf Life, months | 24 |

Typical physical properties are average data and are not to be used as or to develop specifications.

General Considerations for Use

SAG 770 antifoam can be used as received, or after dilution with water or process liquid. For best results, the product should be mixed before use. Dilution can be accomplished by mixing 3 to 10 parts of the selected diluent to 1 part antifoam with gentle stirring until a uniform mixture is obtained. Continued gentle mixing of the diluted antifoam is recommended to ensure product uniformity over extended storage times.

For maximum cost-effectiveness, this antifoam should be prediluted and added continuously at a processing step prior to where foaming is encountered. Suggested starting concentrations are 50 to 400 ppm antifoam, with care being taken in food applications to assure that levels do not exceed the FDA limitations in the final product. Table 3 shows concentrations and parts per million equivalents.

Table 3: SAG 770 antifoam Concentrations and Parts per Million Equivalents

| Concentration of SAG 770 antifoam (from container) | Parts per Million SAG 770 antifoam | |
|-------------------------------------------------------|------------------------------------|---------------------|
| | (As received) | (Active silicone) |
| 1 pint in 1560 gallons | = 80 | = 10 ⁽¹⁾ |
| 10.3 fl. oz. in 100 gallons | = 80 | = 10 ⁽¹⁾ |
| 1 gallon in 1000 gallons | = 1000 | = 125 |
| 1 gallon in 2000 gallons | = 500 | = 62.5 |

(1) FDA Regulation 21 CFR 173.340 limitation Conversion Factors: 1 gallon = 3.785 liters; 1 pint = 0.473 liters; 1 fl. oz. = 29.57 ml

Compared to traditional silicone antifoams, organic defoamers quickly knock down protein- and starch-stabilized foams. However, traditional silicone antifoams are well known for their durable antifoaming efficiency compared to most organic defoamers.

SAG 770 antifoam is a non-traditional silicone antifoam that combines the quick knockdown of organic defoamers (Table 1) with the durability of silicone antifoams (Table 2), providing excellent foam control in protein- and starch-stabilized foams.

Table 1: Foam Knockdown Efficiency of SAG 770 Foam Control Agent Compared to Typical Silicone Antifoam and Organic Defoamer in Protein Foam (1% Albumin)

| Foam Control Agent | Time to Knock Down 20 mL of Foam with Equal Weights of Antifoam, sec |
|----------------------------|----------------------------------------------------------------------|
| Typical Silicone Antifoam | 90 |
| Typical Organic Defoamer | 8 |
| SAG 770 Foam Control Agent | 9 |

Table 2: Durability of SAG 770 Foam Control Agent Compared to Typical Silicone Antifoam and Organic Defoamer in Protein Solutions (1% Albumin)

| Foam Control Agent | Wt. of Antifoam in 200 mL of Solution, g | Foam Weight Generated at 30 sec of Sparging, mL |
|----------------------------|------------------------------------------|-------------------------------------------------|
| Control | 0 | 1000 |
| Typical Organic Defoamer | 0.1 | 440 |
| Typical Silicone Antifoam | 0.1 | 100 |
| SAG 770 Foam Control Agent | 0.1 | 30 |

Note: Test data. Actual results may vary.

Regulatory Compliance

FDA

Compositionally compliant with 21 CFR 173.340 and is appropriate for consideration for use as a defoaming agent in processing foods in accordance with the conditions specified and limitations imposed by this regulation. Please consult the FDA regulations for specifications and limitations, which may apply. The customer has the sole responsibility for determining that their product complies with all applicable FDA specifications and limitations and is fit for food contact use.

USDA

May be considered for use in egg washing, fat rendering, hog scalding, curing pickles, and in the preparation of soups and stews.

Kosher Certification

Manufactured under the supervision of the Kashruth Division of the Union of Orthodox Jewish Congregations of America, and is kosher and pareve when bearing the O.U. symbol of certification on the label. The product is kosher for Passover.

Halal Certified

This product is produced under the supervision of the Islamic Food and Nutrition Council of America (IFANCA). This product is in compliance with the halal requirements under Islamic laws.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas

Latin America

**EMEAI- Europe, Middle
East, Africa & India**

ASIA PACIFIC

| | | | |
|-------------------------|------------------|------------------------------------------------------|------------------|
| +1 800 295 2392 | Brazil | Europe | China |
| Toll free* | +55 11 4534 9650 | +390510924300 | 800 820 0202 |
| +704 805 6946 | Direct Number | Direct number | Toll free |
| Direct Number | | | +86 21 3860 4892 |
| | | | Direct number |
| *All American countries | Mexico | India, Middle East & Africa | Japan |
| | +52 55 2169 7670 | + 91 44 71212207 | +81 3 5544 3111 |
| | Direct Number | Direct number* | Direct number |
| | | *All Middle Eastern countries, Africa, India, | Korea |
| | | | +82 2 6201 4600 |

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under

end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*SAG™ is a trademark of Momentive Performance Materials Inc.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.