

SilForce™ SS8010 Release Coating

SilForce* SS8010 Release Coating

Description

Silforce SS8010 release coating is a catalyst solution used with the Silforce SS4331 solvent-dispersion addition cure release coating system. SilForce SS4331 is a solvent solution of reactive dimethyl siloxane polymers found useful as a release coating on paper, foil and plastic substrates. The dispersion is one component of a three component, platinum addition cure system. Silforce SS8010 platinum catalyst is the second component. The level of SS8010 catalyst in the formulated bath may be either increased or decreased from the standard SS8010 catalyst level to affect processing or reduce cost. SilForce SS4300C methyl-hydrogen siloxane crosslinker is the third component.

The SS4331 system gives excellent bath life at solids levels typically used in dispersion coating. A wide variety of organic solvents may be used in dilution of the bath with aliphatic solvents providing the maximum bath life.

Key Features and Benefits

- Premium release
- Low temperature/high speed cure
- Long bath life
- Non-blocking
- Capable of high solids coating
- Good adhesion to plastic substrates
- Formulating flexibility

Typical Physical Properties

Property	SS4331	SS8010	SS4300C
Silicone Solids, %	29-31	NA	94-100
Volatiles, %	69-71	greater than 99	0-6
Specific Gravity @ 25C(77F)	0.8	0.9	1.01
Density, lbs/gal	6.7	7.6	8.34
Viscosity, cps @ 25C(77F)	8,000-16,000	NA	15-30
Flashpoint, Pensky-Martens (350) Closed Cup °C(°F)	10(50)	4(40)	177(350)
Solvent	VM& P Naphtha	Toluene	None

NA - Not Applicable

Patent Status

Standard copy to come

Product Safety, Handling and Storage

The warranty period is 12 months from date of shipment from Momentive Performance Materials if stored in the original unopened container at 25C (77F).

Standard copy to come

Processing Recommendations

APPLICATION PROCEDURES

SS4331 silicone dispersion may be applied by any of the conventional methods now used for solvent based silicone release products. They include direct gravure, Mayer rod, reverse roll and roll coating.

Heat should be applied immediately after coating to evaporate solvent and initiate cure.

The SS4331 release coating system contains a platinum catalyst which is sensitive to contamination. Potential contaminants include conventional tin catalysts, rust, sulfur

compounds and amines. It is therefore recommended that all coating equipment be cleaned and inspected for possible sources of contamination before use. The preferred situation is to use this system on equipment dedicated to platinum addition cure materials only.

BATH PREPARATION

To prepare the coating bath, the following procedure is suggested:

1. Dilute the SS4331 dispersion to the desired silicone concentration with solvent and stir until completely dispersed. For maximum bath life, an aliphatic solvent is suggested.
2. Add the required amount of SS8010 platinum catalyst and mix thoroughly. See Table 1.
3. For applications requiring tighter release a Controlled Release Additive such as SS4335 or SL4405 or SL4406 additive may be added at this step. Mix thoroughly. See Momentive Performance Materials data sheets on these products for other properties and formulations.
4. Add the required amount of SS4300C cross-linker. See Table 1. The bath is now ready to use.

TABLE 1: BATH FORMULATION OPTIONS

	Lower Cost	Standard	Lower Temp/ Faster Cure
SS4331	100	100	100
Solvent		As Required	
SS8010	1.4	1.8	2.2
SS4300C	1.0	1.0	1.0

BATH LIFE

The Bath Life of these systems is influenced by a number of factors, each of which is controllable. These factors and their effect are listed in Table 2.

TABLE 2: FACTORS AFFECTING BATH LIFE

Factor	Effect	Controls
% Solids of Bath	- High Solids shorten bath life - Low Solids extend bath life	Scale batch size and % solids to meet production requirements.
Bath Temperature	- Higher temps shorten bath life	Provide cooling to the bath.
Platinum Level (as SS8010)	- Higher Platinum levels shorten bath life - Lower Platinum levels extend bath life	Scale batch size & platinum level to meet production requirements. Add additional inhibitor to extend bath life.
Solvent Type	- Aromatic Solvents shorten bath life - Aliphatic Solvents extend bath life (SEE TABLE 3)	Select solvent to meet production requirements.

TABLE 3: VISCOSITY BUILD VS. % SOLIDS

SS4331	100	67	33	33	17
Toluene	---	33	67	---	83
Hexane	---	---	---	67	---
SS8010	1.4	0.93	.47	.47	.24
SS4300C	1.0	.67	.33	.33	.17
% Solids	30	20	10	10	5
VISCOSITY - CPS INITIAL	14800	2300	130	58	20
10 minutes	Gelled	4800	---	---	---
15 minutes		7200	---	---	---
20 minutes		13000	200	85	22
1 hour			270	100	23
2 hours			380	130	23
4 hours			610	170	27
5 hours				210	---
7 hours					28
22 hours					40

Note: Ratio of SS4331, SS8010 and SS4300C is constant in all these formulations.

Limitations

Standard copy to come

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas

+1 800 295 2392

Toll free*

+704 805 6946

Direct Number

Latin America

Brazil

+55 11 4534 9650

Direct Number

EMEAI- Europe, Middle East, Africa & India

Europe

+390510924300

Direct number

ASIA PACIFIC

China

800 820 0202

Toll free

+86 21 3860 4892

All American countries	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207 Direct number	Direct number Japan +81 3 5544 3111 Direct number Korea +82 2 6201 4600
-------------------------	--	--	--

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement

contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*SilForce™ is a trademark of Momentive Performance Materials Inc.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.