

SilForce™ UV9388C Release Coating

SilForce* UV9388C Release Coating

Product Description

SilForce UV9388C release coating (iodonium PF6 salt powder – 100% active material) UV photo initiator intended for use in non-silicone applications such as cationic UV cure inks. Silforce UV9388C is easy to use with most cationic curing organic coatings based on cycloaliphatic epoxy, vinyl ether, glycidyl ether, oxetane, epoxidized olefin and epoxidized unsaturated natural oil functional materials. Depending on the color of the ink/coating, a sensitizer can be added into the reactive formulation.

Generally, two to ten parts by weight of SilForce UV9388C photo-initiator is used in the coating or ink formulation, depending on the application and the substrate used.

Upon UV-irradiation, the SilForce UV9388C photo-initiator releases a strong acid which catalyses the polymerization. Due to the structure of the active ingredient in SilForce UV9388C, there is no release of benzene during the polymerization process.

Key Features and Typical Benefits

- High reactivity – efficient photo response
- Antimony (Sb) free photo-initiator
- Non yellowing properties at aging in white inks
- Excellent solubility in epoxy resins, polymers and inks
- Efficient UV cure at two to ten parts by weight
- Superior shelf life stability
- No release of benzene during UV curing process
- Suitable for all colours (ink, varnishes, coatings...)
- 100% active powder material
- Cationic chemistry – no Nitrogen inerting needed (not sensitive to Oxygen)

General Considerations for Use

SilForce UV9388C photo-initiator functions by the UV initiated release of a strong acid, which catalyzes the polymerization / curing of the coating or ink. Generally, 2 to 10 parts by weight of SilForce UV9388C photo-initiator are normally required in the final formulation of the coating or ink. Photo sensitizers, like Thioxanthenes (e.g. isopropylthioxanthone) or anthracenes can be added to the mixture to increase photo response of the SilForce UV9388C photo-initiator. The precise optimum level of SilForce UV9388C is a function of the desired line speed, colour of the ink and coat weight, substrate and UV lamp configuration. When used in ink applications, the optimal amount of sensitizer will to a large extent be dependent on the colour of this resin.

Cure occurs when a catalyzed coating or ink mixture is exposed to focused deep UV light under ambient conditions. This cure will occur efficiently in an open-air atmosphere and inerting with nitrogen (N₂) is not required. Thorough mixing of the SilForce UV9388C photo-initiator into the mixture is critical for proper performance of the coating.

Catalyzed Bath Life

Catalyzed bath life is largely dependent on the other constituents of the final coating or ink. Prolonged exposure to heat above 30°C, and contamination with strong acids or bases can render SilForce UV9388C photo-initiator inactive either by thermal/acidic breakdown or neutralization of the photo-generated acid at the time of cure.

Use and Bath Preparation

UV Lamps

Cationic curing coatings and inks containing SilForce UV9388C photo-initiator are efficiently photocured by deep UV radiation, particularly < 300 nm wavelength. Either ARC or Microwave fired, medium pressure mercury (Hg) vapour lamps are recommended. Fusion systems' H or H+ sources have been found to be well suited for the photo-cure of epoxy resin mixes containing SilForce UV9388C photo-initiator.

Typical Physical Properties

Typical product data values should not be used as specifications. Assistance and specifications are available at the technical service department of Momentive Performance Materials.

Property	SilForce UV 9388C
Appearance	White crystalline powder
Purity, %	>98

Typical properties are average data and are not to be used as or develop specifications

Containers

0.5 kg sample

25 kg pail

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392 Toll free* +704 805 6946 Direct Number	Brazil +55 11 4534 9650 Direct Number	Europe +390510924300 Direct number	China 800 820 0202 Toll free +86 21 3860 4892 Direct number
All American countries	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207 Direct number	Japan +81 3 5544 3111 Direct number
		*All Middle Eastern countries, Africa, India,	Korea +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR

GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*SilForce™ is a trademark of Momentive Performance Materials Inc.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.