

## Silplus™ 30 AS

Heat Cured Elastomer

## **Description**

Silplus 30 AS, 30 duro hardness heat cured silicone rubber compound for compression molding processes, offers a good anti-static property to silicone rubber products.

## **Key Features and Typical Benefits**

- Good anti-static property
- Colorable translucent appearance
- Excellent mechanical properties and heat resistance
- Excellent processability
- Easy coloring

Typical Physical Properties						


TYPICAL UNCURED PROPERTIES					
Appearance		Translucent			
Williams plasticity		150			
TYPICAL CURED PROPERTIES (Press cure 10 min @ 170 °C, Post cure 4h @ 200					
°C)					
TC-8 curing agent	%	0.35			
MECHANICAL PROPERTIES					
Density (23 °C)	Mg/m <sup>3</sup>	1.09			
Linear shrinkage	%	4.2			
Hardness (Type A)		30			
Tensile strength	MPa	8.7			
Elongation	%	760			
Tear strength (Angle)	N/mm	21			
ELECTRICAL PROPERTIES					
Volume resistivity	W·cm	8´10 <sup>12</sup>			
Half-life time of voltage decay	sec	1.2			
STATIC HONESTMETER, 23 °C 50% humidity, Applied voltage: 6kV					

Typical properties are average data and are not to be used as or to develop


## **Potential Applications**

specifications.

- Mobile jacket, keypad cover, keypad watch
- Consumer goods, novelty, accessory
- Industry roller, rubber sheet
- Automobile parts



# Half-life period of voltage decay



### **Availability**

The material is commercially available in a 20kg box.

#### **Patent Status**

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

#### **Product Safety, Handling and Storage**

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

#### Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

#### **Contact Information**

Email

commercial.services@momentive.com

Telephone

Americas Latin America EMEAI- Europe, Middle ASIA PACIFIC East, Africa & India

+1 800 295 2392	Brazil	Europe	China
Toll free*	+55 11 4534 9650	+390510924300	800 820 0202
+704 805 6946	Direct Number	Direct number	Toll free
Direct Number			+86 21 3860 4892
			Direct number
*All American	Mexico	India, Middle East &	Japan
countries	+52 55 2169 7670	Africa	+81 3 5544 3111
	Direct Number	+ 91 44 71212207	Direct number
		Direct number*	
		*All Middle Eastern	Korea
		countries, Africa, India,	+82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

#### **DISCLAIMER:**

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE. SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under

end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\*Silplus™ es una marca comercial de Momentive Performance Materials Inc.

The use of the "TM" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.