

SilForce™ SL6062 Release Coating

Product Description

This thermal solventless release coating is an excellent candidate to consider for kraft, art and open papers, where the porosity is relatively high compared to classical glassine or SCK liners. The high viscosity vinyl polymer can enable the reduction of silicone consumption while maintaining good silicone coverage for stable release performance.

Product References

SilForce SL6062 base polymer

SilForce SL6031 controlled Release Additive ⁽¹⁾

SilForce SL4380 cross-linker for papers ⁽²⁾

SilForce SL6210 controlled release additive

(1) Other CRAs may be considered for this base polymer (please contact technical expert from Momentive for advice) F

(2) Depending on the substrate and/or the processing conditions other cross-linkers can be used

Key Features and Typical Benefits

- Versatile system for open paper substrates (e.g. kraft papers)
- High formulation flexibility
- Enhanced cross-linkers for good anchorage of the release coating
- Potential productivity gain in terms of silicone usage

Potential Applications

The SilForce SL6062 system is compositionally compliant with the following US regulations: 21 CFR 175.320 (resinous and polymeric coatings for polyolefin films),

176.170 (components of paper and paperboard in contact with aqueous and fatty foods), and 176.180 (components of paper and paperboard in contact with dry foods). SilForce SL6031 controlled release additive is compositionally compliant with 21 CFR 175.320 (resinous and polymeric coatings for polyolefin films). The end user has sole responsibility for determining that its product complies with all applicable FDA specifications and limitations and is fit for food contact use.

Typical Physical Properties

Property	SilForce SL6062	SilForce SL6031
Viscosity, mPa•s, 25°C	350 - 450	1500 - 2700
Density, kg/l	0.97	1.04

Typical properties are average data and are not to be used as or develop specifications.

General Considerations for Use

This solventless release coating system can be applied by many of the methods now being used commercially for solventless silicone. These include three roll differential offset gravure and various multiple smooth roll configurations. Heat should be applied immediately after coating to initiate cure. Best results are obtained with zoned ovens. Operating the first oven zone at 90-150 °C will allow the coating to level, forming a continuous film before cure is initiated. Subsequent oven zones should be sufficiently high in temperature to achieve the required web exit temperature. Actual temperatures required for complete cure will be highly dependent on the performance of the oven and machine conditions. In general, minimum web temperature must be maintained for a finite time (= dwell time) to obtain complete cure, such time being dependent on oven length and the line speed.

Typical starting formulations for glassine papers at a catalyst level of 40 ppm

Component	0% CRA	10% CRA	20% CRA
SilForce SL6062 base polymer	96	86	76
SilForce SL6031 controlled release additive	-	10	20
SilForce SL4380 cross-linker for papers	3.1	3.8	4.6
SilForce SL6210 concentrated catalyst	4	4	4

Important Note:

The suggested starting formulation in the table is based on cure optimization. Destabilized (high) release may occur with some adhesives like self-cross-linkage solution acrylics and UV hot melt, at the suggested cross-linker levels. Please contact a Momentive Performance Materials Technical Service Representative for further information.

Bath Life

The working life of an activated bath will vary depending on ambient conditions. In general, the suggested formulation in the table will have a minimum bath life of 4 hours under normal processing conditions.

The thin film bath life of the SilForce SL6062 system is significantly shorter than the thin film bath life of the SilForce SL6600 and SilForce SL6625 systems, therefore we recommend to have a “proper cleaning” of the coating head if the machine is stopped for more than 20 minutes.

At high catalyst level (more than 80 ppm Platinum) bath life with the SilForce SL6062 system can be shorter.

Bath Preparation

To ensure consistent results and maximize bath life, components should be mixed in the following order:

1. Weigh and add SilForce SL6062 system to a clean, rust-free container/mixing vessel
2. Weigh and add the cross-linker (SilForce SL4380 cross-linker for example) to the

above material

3. Agitate thoroughly for 5 minutes to ensure homogeneity
4. Weigh and add the platinum concentrate (SilForce SL6210 concentrated catalyst) to above mix
5. Agitate thoroughly for 10-15 minutes to ensure homogeneity

Bath should be prepared just prior to use.

Coating Weight/Substrates

The optimal coat weight will depend on the hold out of the surface, but generally 0.8-1.4 g/m² will provide a continuous silicone film.

Coat weights can be determined by X-Ray Fluorescence.

Patent Status

本書のいかなる内容も、関連特許が存在しないことを暗示したものではありません。またいかなる特許についても、その権利者による許可なしに、その特許が対象とする発明を実施するための許可、誘因または推奨を構成することはできません。

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392 Toll free*	Brazil +55 11 4534 9650 Direct Number	Europe +390510924300 Direct number	China 800 820 0202 Toll free +86 21 3860 4892 Direct number
All American countries	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207 Direct number	Japan +81 3 5544 3111 Direct number
		*All Middle Eastern countries, Africa, India,	Korea +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE.

EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

* SilForce™は Momentive Performance Materials Inc. の商標です。

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.