

PEarlene™ SiPC MB01 Silicone

Description

PEarlene silicone is a gum-containing master batch for the compounding and/or extruding of certain plastics, copolymers and elastomeric formulations that can help provide improved processability (extrusion rate, mold fill and power consumption) and/or performance (izod impact resistance, especially at low temperatures).

The PEarlene silicone line is a family of functional master batches containing high levels of ultra-high-molecularweight polysiloxane which are melt compounded into a thermoplastic polymer. This product line consists of several silicone gum masterbatches based on PE, PP and PC.

Key Features and Typical Benefits

- Improved lubricity of fabricated part
- Improved izod impact resistance especially at low temperatures
- Increased fabrication line throughput
- Reduced extrusion drive load
- Reduced extruder head pressure
- Reduced energy usage in processing

Typical Physical Properties

Form Uniform	Free flowing pellets
Color	Off-white
Density (gm/cc) at 20 °C	1.20 - 1.22
MFI (230 °C at 2.16 Kg)	2-4g / 10 min

Siloxane Content, %	30
Odor	Essentially odorless
Solubility in Water	Insoluble
Melting Point, °C	270

Typical properties are average data and are not to be used as or to develop specifications.

Polymer Modification:

PEarlene SiPC MB-01 silicone (PC: polycarbonate carrier)

These masterbatches modify the rheological characteristics of the resin or compound, which can allow for increased throughputs in production as well as a reduction in the drive torque and machine head pressure, and at increased levels can improve the surface appearance of the fabricated part and lower the coefficient of friction (CoF) on finished parts. It can also noticeably improve fine molded details and mold release. Typical usage levels are from 0.2% to 1.6% by weight of silicon gum.

Select the carrier compatible with your formulation or check with Momentive Performance Materials for detailed information.

Potential Applications

PEarlene silicone gum-containing masterbatches are free-flowing, dry, pelleted materials and excellent candidates to consider for compounding operations and extrusion-based fabrication processes including:

- Wire and cable extrusion,
- Pipe extrusion,
- Injection and compression molding,
- Blown and cast film,
- Foaming operations (closed and open cell as well as structural); thermoforming.

These masterbatches have shown to be effective in polyolefins (PP, PE and their copolymers) as well as EVA, nylon and PC. The product is manufactured to not contain any halogens.

Improper mixing or the use of the wrong type or wrong level of additive will not result in the expected performance enhancements.

General Considerations for Use

Generally, PEarlene silicone gum masterbatches can be added to the resin or compound during the final melt extrusion or fabrication step, and typically processed on conventional equipment under the same processing conditions recommended for the base resins and/or compounds. While no special conditions or process modifications are generally required, PEarlene silicone gum masterbatches must be melt processed under conditions that will assure a high level of homogeneity in the final product.

At addition levels between 0.2% to 1.6% of PEarlene silicone masterbatches by weight of silicone gum, the resin and/or compound will typically be rheologically modified, which can enable better mold flow and fill, replication of fine mold details with more precision, and easier part release without the need for a separate mold release agent.

The addition of PEarlene silicone gum masterbatches typically will improve the coefficient of friction (CoF) of the final part, enhance the surface finish, abrasion resistance, and mar resistance of the fabricated part and render the final part less subject to warpage. Generally, the tensile and elongation properties of the final products will only be slightly affected by the PEarlene silicone gum masterbatches, even at the highest recommended level of addition, and the impact resistance will be improved especially at low temperatures. The product is essentially odorless and colorless (though some grades are off-white), and will normally not affect the odor or color of the material it is added to, also after final fabrication.

Process benefits may include an increase in throughput and a reduction in machine torque and pressure in screw slippage, potentially lowering manufacturing variable costs. The process may also benefit from less frequent shut downs for screw, screen, die and tooling cleanup, as well as less effort being required for the cleaning of machine parts.

Please note that it might be necessary to increase the extrusion speed and reduce machine temperature settings to achieve the full benefit of the additional throughput

when using these masterbatches.

Compounds containing PEarlene silicone masterbatches may be available from your resin or compound supplier.

Patent Status

여기에 포함된 어떠한 내용도 관련 특허가 없음을 의미하거나 특허 소유자의 허가 없이 특허에서 다루는 발명을 실행하기 위한 허가, 유도 또는 권고를 구성하는 것으로 해석되어서는 안됩니다.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392 Toll free*	Brazil +55 11 4534 9650 Direct Number	Europe +390510924300 Direct number	China 800 820 0202 Toll free +86 21 3860 4892 Direct number
+704 805 6946 Direct Number	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207 Direct number*	Japan +81 3 5544 3111 Direct number
*All American countries		*All Middle Eastern countries, Africa, India,	Korea +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and

perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*PEarlene™는 Momentive Performance Materials Inc.의 상표입니다.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.