

Silplus™ 40 HT

Description

Silplus* 40 HT heat cured silicone elastomer is an excellent candidate to consider for press- and injection-molding, calendaring and extrusion. Its increased heat stability can provide excellent resistance for applications exposed to high temperature.

Key Features and Typical Benefits

- Very good heat resistance up to 300 °C
- Easily blendable

Typical Physical Properties

Typical properties of the uncured base compound			
Appearance			Colorless
Physical State			Solid
Density	DIN 53 479 A	g/cm ³	1.10
ML (4) 25 °C		M.U.	26

Typical properties of the Vulcanized Rubber			
100 pbw Silplus 40 HT elastomer with 1.5 pbw bis-(2,4-dichlorobenzoyl)peroxide (50%). Vulcanization conditions: 10min/125°C, post-curing: 6h/200°C in hot air			
Hardness	DIN 53 505		40
Tensile strength	DIN 53 504 S2	MPa	6.5
Elongation at break	DIN 53 504 S2	%	450
Tear strength	ASTM D 624 die B	N/mm	10
Compression Set (22h/175 °C)	ISO 815	%	40

Using other peroxides might result in different mechanical properties. Diacyl-peroxides like di(2,4-dichlorobenzoyl)peroxide are non vinyl specific cross link peroxides (higher

cross link density). Diaryl-peroxides like dicumyl-peroxide or dialkyl-peroxides like 2,5-dimethyl-2,5-di(tert.butylperoxy)hexane are vinyl specific cross link peroxides (lower cross link density).

Typical Properties after Heat aging (Change)		
10 days @ 200 °C		
Hardness	Δ Shore A	-4
Elongation at break	Δ %	-7%
Tensile strength	Δ MPa	-4%
10 days @ 250 °C		
Hardness	Δ Shore A	-3
Elongation at break	Δ %	-31%
Tensile strength	Δ MPa	-29%
10 days @ 300 °C		
Hardness	Δ Shore A	+18
Elongation at break	Δ %	-76%
Tensile strength	Δ MPa	-51%

Typical properties are average data and are not to be used as or to develop specifications.

Potential Applications

Silplus 40 HT heat cured elastomer is an excellent candidate to consider for applications where the final compound is regularly or continuously exposed to high temperatures. Potential applications include:

- Moldmaking for rotocasting
- High temperature hoses and bellows
- Aviation and aerospace applications

Processing Considerations

Crosslinking can be carried out with most peroxides commonly used for the press molding and extrusion process. If the goods are to be vulcanized without pressure, e.g. in hot air or in an infrared radiation tunnel, bis-(2,4-dichlorobenzoyl)peroxide (50%) is

recommended. The dosage ranges between 1-2 pbw of crosslinking agent on 100 pbw of base compound. In general, good results have been achieved by the intermediate dosage of 1.5 pbw.

While the crosslinking agent is being incorporated, the temperature of the compound should not exceed 40 °C so the rolls of the mixing mill should always be well cooled. The achievable compression set with bis-(2,4-dichlorobenzoyl)peroxide is generally less satisfactory than with dicumyl peroxide or comparable products. To vulcanize goods in a press or in steam recrystallized dicumyl peroxide is recommended. Instead of dicumyl peroxide, corresponding proportions of other peroxides (e.g. with less odor) may be considered.

Heat-stable compounds in higher hardness typically can be achieved with Silplus 70 HT heat cured elastomer as blending partner.

Regulatory Compliance

Silplus 40 HT heat cured elastomer is not compositionally compliant with 21 CFR §177.2600 or BfR XV.

Packaging

Silplus 40 HT elastomer is available in 500 kg boxes.

Patent Status

여기에 포함된 어떠한 내용도 관련 특허가 없음을 의미하거나 특허 소유자의 허가 없이 특허에서 다루는 발명을 실행하기 위한 허가, 유도 또는 권고를 구성하는 것으로 해석되어서는 안됩니다.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers)

may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392 Toll free* +704 805 6946 Direct Number	Brazil +55 11 4534 9650 Direct Number	Europe +390510924300 Direct number	China 800 820 0202 Toll free +86 21 3860 4892 Direct number
All American countries	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207 Direct number *All Middle Eastern countries, Africa, India,	Japan +81 3 5544 3111 Direct number Korea +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR

OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Silplus™는 Momentive Performance Materials Inc.의 상표입니다.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.