

Niax* catalyst A-1

Niax* catalyst A-1

Description

Niax catalyst A-1 contains 70 percent bis(2-dimethylaminoethyl) ether, one of the most active urethane foam amine catalysts known. As a matter of convenience, the pure amine ether has been diluted with 30 weight percent dipropylene glycol to facilitate metering and to permit the use of conventional quantities in foam formulations.

Typical Physical Properties

Specific Gravity at 20/20°C (68/68°F)	0.9022
Viscosity at 20°C (68°F), cP	4.1
Freezing Point	Sets to glass below -80°C (-112°F)
Vapor Pressure, mm Hg	0.01
Solubility in Water at 20°C (68°F)	Complete
Solubility in Benzene at 20° (68°F)	Complete
Refractive Index, n _D 25°C	1.4346
Flash Point, °C (°F)	74 (165)
Pensky-Martens Closed Cup ⁽¹⁾	

(1) ASTM Method D 93

Catalytic Activity

The basic chemical reactions important in the polyether foaming process are the polyol/isocyanate reaction and the water/isocyanate reaction. Table 1 shows how Niax catalyst A-1 compares to various amine catalysts in promoting these two basic reactions. In the polyol/isocyanate (alcohol/isocyanate) reaction, Niax catalyst A-1 gives a specific rate constant that is about 10 percent higher than a similar blend of triethylene diamine, the next most active amine. In the water/isocyanate reaction, however, Niax catalyst A-1 has a specific rate constant that is 50 percent greater than triethylenediamine, the next most active amine.

The strong catalytic effect of Niax catalyst A-1 toward the water/isocyanate reaction facilitates the balancing of the catalysis of the polyol/isocyanate reaction by small variations in the stannous octoate level. This control is important in the production of commercial open-celled, split-free, flexible urethane foam. The level of Niax catalyst A-1 can be adjusted over a wide range to permit control of foam rise time without a sacrifice in tin operating range.

Table 1: Reaction Rate Constants of Niax Catalyst A-1 Compared to Conventional Amine Catalysts

Alcohol/Isocyanate Reactions ⁽¹⁾	Specific Rate Constant ⁽²⁾ , Alcohol/Isocyanate Reactions(1) Ka/Ca (min ⁻¹)
Niax Catalyst A-1	56
Triethylenediamine	49
N,N-Dimethylethanolamine	10
N-Methyl Morpholine	7.5
N-Ethyl Morpholine	5.0
Water/Isocyanate Reactions ⁽³⁾	
Niax Catalyst A-1	158
Triethylenediamine	98
N,N-Dimethylethanolamine	68
N-Methyl Morpholine	14
N-Ethyl Morpholine	10

(1) Equal parts stannous octoate used with each amine

(2) Kinetic data obtained with a model reaction system consisting of butanol and phenyl isocyanate at 25°C in a solvent blend of 90 percent toluene and 10 percent dimethylformamide

(3) Kinetic data obtained with a model reaction system consisting of water and phenyl isocyanate at 25°C in a solvent blend of 90 percent toluene and 10 percent dimethylformamide

Processing Recommendations

Performance in Urethane Foam

Niax catalyst A-1, when used alone or as part of the amine catalyst system, helps improve the processing characteristics and physical properties of the following types of flexible foams:

- High-density unfilled foam
- Filled foam
- High-load-bearing flexible foam
- Low-density foam
- High Resilience molded foam

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains

an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

For product prices, availability, or order placement, contact our customer service at Momentive.com/CustomerService/

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.