

LSR Topcoat

LSR Topcoat

Description

LSR Top Coat is a two-component low friction, protective translucent matte coating for consideration in applications such as respiratory face masks or orthopaedic devices, industrial seals or keypads. This material can be applied by spraying, brushing or dipping on surfaces that are dust and grease free but otherwise untreated. The LSR Top Coat can be cured very quickly at high temperatures (100°C to 180°C) in a ventilated hot-air oven.

Key Features and Benefits

- Provides translucent matte finish coating
- Good adhesion to Momentive's Silicones elastomer substrates
- Reduces the surface coefficient of friction (COF) of silicone elastomer substrates
- Reduces surface tackiness of RTV substrates
- Reduces surface dust pick up
- VOC (Volatile Organic Compound) free
- Biocompatible (USP Class VI requirements)
- Can be colored by using silicone compatible pigments
- Elastic properties may reduce the risk of microcracking on elastomeric surfaces under mechanical stress

Typical Physical Properties

Properties	Typical Data
------------	--------------

Color		Translucent matte finish coating	
Brookfield Viscosity 1 cp		~1600 cP-sec.	
Specific Gravity @ 25°C, gms / cc		1.03	
Pot Life of 1:1 Ratio Mixture @ 25°C ^[1]		~4-6 hours	
Refractive Index		1.41	
Flow-cup Viscosity	DIN EN ISO 2431 at 20°C	30-40 sec.	ca. 33
Abrasion Resistance	Norman Tool Tester. 175 g. paper, continuous mode, at 80 µ dry film thickness	cycles	80-100
<p>[1] The pot life of the mixture can be increased to 2-3 days if the mixture is kept well below room temperature.</p> <p>Apply the coating immediately after mixing to avoid viscosity build up and ingredient settlement over time.</p> <p>The pot life of the mixture of the two components {mixing ratio 1:1} at 20°C is three days.</p> <p>Increased temperature reduces the pot life.</p>			

Potential Applications

Typical applications for consideration are cell phone covers, consumer and healthcare grips and handles, connector seals, automotive interior applications, and any other area where the bulk properties of silicone are desired coupled with a surface exhibiting a lower coefficient of friction.

Patent Status

Standard copy to come

Product Safety, Handling and Storage

Standard copy to come

Limitations

Standard copy to come

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392 Toll free*	Brazil +55 11 4534 9650 Direct Number	Europe +390510924300 Direct number	China 800 820 0202 Toll free +86 21 3860 4892 Direct number
+704 805 6946 Direct Number			
All American countries	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207 Direct number	Japan +81 3 5544 3111 Direct number
		*All Middle Eastern countries, Africa, India,	Korea +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED

HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Silopren™ é uma marca registrada da Momentive Performance Materials Inc.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.