

Silwet™ DA-33

Performance Additive

Description

Silwet DA performance additives are FDA compliant additive that improve the performance of brown stock pulp defoamers used in the manufacture of paper and paperboard for indirect food contact. They enhance the dispersion and efficiency of formulated defoamers and also act as defoamers above their cloud point. In addition, they increase water drainage through pulp mats by significantly reducing entrained air and associated foam. Silwet DA additives are highly compatible with organic defoamers and are formulated without dioxin.

Key Features and Typical Benefits

- Permitted under FDA regulation 21 CFR 176.210 ⁽¹⁾
- Improved dispersion and efficiency of other defoamer actives
- Cloud point defoamers
- Enhance pulp drainage
- Dioxin-free
- Easy to use in formulation
- Halal Certified ⁽²⁾

(1) Note: Please consult the FDA regulations for specifications and limitations, which may apply. The customer has the sole responsibility for determining that their product complies with all applicable FDA specifications and limitations and is fit for food contact use.

(2) This product is produced under the supervision of the Islamic Food and Nutrition Council of America (IFANCA). This product is in compliance with the halal requirements under Islamic laws.

Typical Physical Properties

Silwet DA performance additives are made up of 100-percent active products. They are uncapped, polyether-modified silicone copolymers, described by CAS #68937-55-3.

Silwet Performance Additive

| Property | DA-33 | DA-40 | DA-63 |
|--|------------|----------------|-----------|
| Cloud Point, °F (°C) | 104 (40) | 77 (25) | <77 (<25) |
| Viscosity at 25°C, cSt | 3500 | 1000 | 1100 |
| Flash Point, °F (°C) | | | |
| Pensky-Martens Closed Cup | 275 (135) | 149 (ASTM D93) | 290 (143) |
| Cleveland Open Cup | >300 (149) | 480 (249) | 550 (228) |
| EO ⁽¹⁾ : PO ⁽²⁾ Weight Ratio of Pendant Groups | 40:60 | 20:80 | 20:80 |
| Molecular Weight, avg. | 30,000 | 12,000 | 17,000 |

Typical physical properties are average data and are not to be used as or to develop specifications.

(1) Ethylene oxide

(2) Propylene oxide

Silwet DA performance additives are based on silicone copolymer technology. Ethylene and propylene oxides form the building blocks of the pendant groups used to modify the physical properties of the silicone backbone.

Potential Applications

Silwet DA performance additives can be considered for use to boost the performance of defoamers used in the Kraft pulping process during brown stock washing and screening. They can also enhance the effectiveness of defoamers used to reduce entrained air in paper-processing white water.

Advantages

Silwet DA performance additives offer a number of important advantages to the pulp and paper processor:

FDA Regulated Additives

Silwet DA-33, DA-40, and DA-63 are compositionally compliant with FDA 21 CFR 176.210, which identifies substances that may be used in the manufacture of paper and paperboard for indirect food contact.

Improved Dispersion

By improving the dispersion of brown stock pulp defoamers, Silwet DA performance additives can help improve the efficiency of other defoamer actives in formulated products.

Cloud Point Defoaming

At temperatures above their cloud points, Silwet DA performance additives aid in the foam control of aqueous processes. This performance typically improves dramatically as one goes from Silwet DA-33 to DA-40 to DA-63 performance additives.

Enhanced Pulp Drainage

Two types of foaming characterize pulp and paper processes: surface foam and foam related to entrained air. Entrained air retards water drainage, which increases paper processing costs downstream. Silwet DA performance additives can help significantly reduce entrained air and improve drainage efficiency.

Easy to Use, Compatible Additives

Silwet DA performance additives are liquid products that may readily be incorporated in defoamer formulations. Furthermore, they are compatible with most commonly used organic compounds, such as mineral oil, fatty esters or silicone oil.

General Considerations for Use

Silwet DA performance additives should be added at 0.2-1.5 wt % to your formulated defoamers to improve dispersibility. At slightly higher addition levels, they contribute to the defoaming capability of your product. Call your Momentive Performance Materials Technical Representative for additional assistance.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

| Americas | Latin America | EMEAI- Europe, Middle East, Africa & India | ASIA PACIFIC |
|-------------------------|----------------------|---|---------------------|
| +1 800 295 2392 | Brazil | Europe | China |
| Toll free* | +55 11 4534 9650 | +390510924300 | 800 820 0202 |
| +704 805 6946 | Direct Number | Direct number | Toll free |
| Direct Number | | | +86 21 3860 4892 |
| | | | Direct number |
| *All American countries | Mexico | India, Middle East & Africa | Japan |
| | +52 55 2169 7670 | + 91 44 71212207 | +81 3 5544 3111 |
| | Direct Number | Direct number* | Direct number |

***All Middle Eastern Korea**
countries, Africa, India, +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Silwet™是 Momentive Performance Materials Inc. 的商标

The use of the “™” symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.